

Densurf HR 700A

Silicone Resin

Content Publish Date: 21.05.2026
Content Revision Date: 21.05.2026
Content Revision No : 001

PRODUCT DESCRIPTION

Densurf HR 700A is a methyl-polysiloxane resin that can be cured at the ambient conditions with help of the catalyst.

The curing reaction is catalyzed by the tetra-n-butyl titanate (Densurf TBT).

APPLICATIONS & KEY FEATURES

It provides thermal resistance up to the 600 - 650 °C when it is formulated correctly.
It is used for the heat and the corrosion resistant solvent-based coatings.

The main application areas of the Densurf HR 700A are:

- Heat Resistant Applications
- General Industrial Paints

SOLUBILITY

Water	Ethanol
	
N-Butyl Acetate	Isobutanol
	
Xylene	Methoxy Propyl Acetate
	
	
Soluble	Not Soluble

**Detailed knowledge about the suitable diluents can be asked to the technical support team. The provided diluents are the references according to the most common application areas.

STORAGE

Please store the unopened packaging between 5°C - 35°C.
The shelf life is at least 12 months for unopened packagings.
Close the packaging cap tightly after use.

WARNING! Keep away from the acids, the heat and the moisture.

SPECIAL NOTES

Densurf HR 700A provides an excellent hydrophobicity and the corrosion-protection.

It has very low viscosity and can be cured with both the catalyst and the heat.

TECHNICAL PROPERTIES

- Chemical Structure: Methyl-polysiloxane resin
- Appearance: Transperent/hazy liquid
- Density (20°C): 1,11 ± 0,02 g/mL
- Solid Content (10 mins., 160°C): 100,00 %

SYSTEM

Long Oil Alkyd Resins	Polyester Resins
	
Short Oil Alkyd Resins	Thermoplastic Acrylic
	
Solvent-Based Epoxy Resins	Acrylic Polyol Resins
	
	
Suitable	Not Suitable

**Detailed knowledge about the compatible systems can be asked to technical support team. The provided systems are the references according to the most common application areas.

DOSAGE

Recommended amount: 30.00 - 50.00 % (by weight as supplied based on the total formulation)

Note: Amounts mentioned above are just a recommendation. Please make laboratory tests to specify the optimum amounts.

The Densurf TBT should be added into the paint system before the application.

The catalyst dosage (Densurf TBT) should be 0.80–1.20% based on the active solid content of the resin.

PROCESS RECOMMENDATION

It can be cold-blended with the suitable organic resins. Surface pre-treatment is needed.

It completes its touch-free dry within the 1 hour after the application.

It needs to wait for the 7 days at the ambient condition for the total curing.