

Densurf DA 4010

Wetting & Dispersing Agent

Content Publish Date: 21.05.2026
Content Revision Date: 21.05.2026
Content Revision No : 001

PRODUCT DESCRIPTION

Densurf DA 4010 is a solvent-free high molecular weight polymer used as a wetting and dispersing agent.

It supports the dispersion stability with the steric effects.

APPLICATIONS & KEY FEATURES

Densurf DA 4010 is highly effective for the pigment wetting and helps durability of the final product. Densurf DA 4010 improves the color properties and increase the color strength.

The main application areas of the Densurf DA 4010 are:

- Wood Coatings
- Printing Inks
- General Industrial Paints
- Pigment Pastes

SOLUBILITY

Water	Aliphatic Hydrocarbons
	
N-Butyl Acetate	N-Butanol
	
Xylene	Methoxy Propyl Acetate
	
	
Soluble	Not Soluble

**Detailed knowledge about the suitable diluents can be asked to the technical support team. The provided diluents are the references according to the most common application areas.

STORAGE

Please store the unopened packaging between 5°C - 35°C. The shelf life is at least 24 months for unopened packagings. Close the packaging cap tightly after use.

WARNING! Keep away from the acids, the heat and the moisture.

SPECIAL NOTES

Densurf DA 4010 is developed for the carbon black pigment especially for the black jetness.

It has an excellent compatibility with all kind of solid particle special for the direct grinding.

TECHNICAL PROPERTIES

- Chemical Structure: Polyether modified copolymer
- Appearance: Clear brown liquid
- Acid Value: 6.00 ± 2.00 mg KOH/g
- Amine Value: 15.00 ± 2.00 mg KOH/g
- Density (20°C): 1.57 ± 0.02 g/mL
- Solid Content (10 mins., 160°C): 98.50 ± 1.00 %

SYSTEM

Thermoplastic Acrylic Resins	Polyester Resins
	
Acrylic Polyol Resins	Aldehyde Resins
	
Epoxy Resins	Ketonic Resins
	
	
Suitable	Not Suitable

**Detailed knowledge about the compatible systems can be asked to technical support team. The provided systems are the references according to the most common application areas.

DOSAGE

Titanium dioxide: 0.50 - 2.00 % (by weight as supplied based on the pigment amount)
Inorganic pigments: 5.00 - 10.00 % (by weight as supplied based on the pigment amount)
Extenders: 0.30 - 0.80 % (by weight as supplied based on the pigment amount)
Co-grinding systems: 0.30 - 1.00 % (by weight as supplied based on the pigment amount)
Organic pigments: 8.00 - 20.00 % (by weight as supplied based on the pigment amount)
Carbon Black: 10.00 - 30.00 % (by weight as supplied based on the pigment amount)

PROCESS RECOMMENDATION

The additive should be added into the millbase and premixed in the binder or solvent before the pigment is added.