

Densurf DA 202

Wetting Agent

Content Publish Date: 21.05.2026
Content Revision Date: 21.05.2026
Content Revision No : 001

PRODUCT DESCRIPTION

Densurf DA 202 is a surface active material used as a wetting agent.

It supports the dispersion stability with the steric effects.

APPLICATIONS & KEY FEATURES

Densurf DA 202 is a highly effective for pigment wetting. Excellent pigment wetting helps to the viscosity reduction and improves the color properties of the system.

The main application areas of the Densurf DA 202 are:

- Road Markings
- Protective Coatings
- General Industrial Paints

SOLUBILITY

Water	Aliphatic Hydrocarbons
	
N-Butyl Acetate	N-Butanol
	
Aromatic Hydrocarbons	Ethanol
	
	
Soluble	Not Soluble

**Detailed knowledge about the suitable diluents can be asked to the technical support team. The provided diluents are the references according to the most common application areas.

STORAGE

Please store the unopened packaging between 5°C - 35°C. The shelf life is at least 24 months for unopened packagings. Close the packaging cap tightly after use.

WARNING! Keep away from the acids, the heat and the moisture.

SPECIAL NOTES

Densurf DA 202 can be used as a co-dispersant especially in the synthetic paints.

It has an excellent viscosity reduction effect for the methacrylate based resin containing systems.

TECHNICAL PROPERTIES

- Chemical Structure: Surface active compounds
- Appearance: Opaque Light Yellow liquid
- Acid Value: 34.00 ± 3.00 mg KOH/g
- Density (20°C): 1.08 ± 0.02 g/mL
- Solid Content (10 mins. 160°C): 57.00 ± 2.00 %

SYSTEM

Long Oil Alkyd Resins	Rapid Alkyd Resins
	
Short Oil Alkyd Resins	Nitrocellulose Resins
	
Medium Oil Alkyd Resins	Acrylic Polyol Resins
	
	
Suitable	Not Suitable

**Detailed knowledge about the compatible systems can be asked to technical support team. The provided systems are the references according to the most common application areas.

DOSAGE

Titanium dioxide: 0.50 - 2.00 % (by weight as supplied based on the pigment amount)
Inorganic pigments: 5.00 - 10.00 % (by weight as supplied based on the pigment amount)
Extenders: 0.30 - 0.80 % (by weight as supplied based on the pigment amount)
Co-grinding systems: 0.30 - 1.00 % (by weight as supplied based on the pigment amount)

PROCESS RECOMMENDATION

The additive should be added into the millbase and premixed in the binder or solvent before the pigment is added.