

Densurf DA 4040

Wetting & Dispersing Agent

Content Publish Date: 21.05.2026
Content Revision Date: 21.05.2026
Content Revision No : 002

PRODUCT DESCRIPTION

Densurf DA 4040 is a solvent-based high molecular weight polymer solution used as a wetting and dispersing agent.

It supports the dispersion stability with the steric effects

APPLICATIONS & KEY FEATURES

Densurf DA 4040 is a highly effective for pigment wetting and helps durability of the final product. Densurf DA 4040 improves the levelling and the gloss properties.

The main application areas of the Densurf DA 4040 are:

- Automotive Paints
- General Industrial Paints
- Protective Coatings
- Floor Coatings

SOLUBILITY

Water	Aliphatic Hydrocarbons
	
N-Butyl Acetate	N-Butanol
	
Xylene	Methoxy Propyl Acetate
	
	
Soluble	Not Soluble

**Detailed knowledge about the suitable diluents can be asked to the technical support team. The provided diluents are the references according to the most common application areas.

STORAGE

Please store the unopened packaging between 5°C - 35°C. The shelf life is at least 24 months for unopened packagings. Close the packaging cap tightly after use.

WARNING! Keep away from the acids, the heat and the moisture.

SPECIAL NOTES

Densurf DA 4040 is developed for the inorganic pigments and filler for the stability maintenance.

It can be used to increase the levelling and can provide a high covering in the thin film applications.

TECHNICAL PROPERTIES

- Chemical Structure: Polyether modified copolymer
- Appearance: Clear brown liquid
- Acid Value: 4.20 ± 2.00 mg KOH/g
- Amine Value: 6.20 ± 2.00 mg KOH/g
- Density (20°C): 0.98 ± 0.02 g/mL
- Solid Content (10 mins., 160°C): 40.00 ± 2.00 %
- Solvent: Methoxy Propyl Acetate : N-Butyl Acetate (1 : 1)

SYSTEM

Thermoplastic Acrylic Resins	Polyester Resins
	
Acrylic Polyol Resins	Aldehyde Resins
	
Epoxy Resins	Ketonic Resins
	
	
Suitable	Not Suitable

**Detailed knowledge about the compatible systems can be asked to technical support team. The provided systems are the references according to the most common application areas.

DOSAGE

Titanium dioxide: 0.50 - 2.00 % (by weight as supplied based on the pigment amount)
Inorganic pigments: 5.00 - 10.00 % (by weight as supplied based on the pigment amount)
Extenders: 0.30 - 0.80 % (by weight as supplied based on the pigment amount)

PROCESS RECOMMENDATION

The additive should be added into the millbase and premixed in the binder or solvent before the pigment is added.